

Lewatit® MonoPlus M 500 MB is a strongly basic, gelular anion exchange resin with beads of uniform size (monodisperse) based on a styrene-divinylbenzene copolymer. Due to the monodisperse bead size distribution (uniformity coefficient max. 1.1) and a special manufacturing process this resin type is tailor-made for mixed bed application in make-up water systems. The special crosslink rate leads to a very high regeneration efficiency paired with a reduced rinse water demand.

Lewatit® MonoPlus M 500 MB is especially applicable for:

» mixed bed application in combination with **Lewatit® MonoPlus S 108 H**

Lewatit® MonoPlus M 500 MB is adding special features to the resin bed:

- » a special bead size distribution ensuring a perfect separation of resin components without cross-contamination
- » a good utilization of the total capacity
- » a low rinse water demand
- » homogenous throughput of regenerants, water and solutions; therefore a homogenous working zone
- » sharply contrasting colours

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Liquid Purification Technologies (LPT).

General Description

Ionic form as shipped	Cl ⁻
Functional group	Quaternary amine, type I
Matrix	Crosslinked polystyrene
Structure	Gel
Appearance	Yellow, translucent

Specified Data

	metric units	
Uniformity Coefficient	max.	1.1
Mean bead size	mm	0.62 (+/- 0.05)
Total capacity	min. eq/l	1.3

Physical and Chemical Properties

		metric units	
Bulk density	(+/- 5 %)	g/l	690
Density		approx. g/ml	1.08
Water retention		wt. %	48 - 55
Volume change	Cl ⁻ --> OH ⁻	max. vol. %	22
Stability	at pH-range		0 - 14
Storability	of the product	max. years	2
Storability	temperature range	°C	-20 - +40

This document contains important information and must be read in its entirety.

Recommended Operating Conditions*

		metric units	
Operating temperature		max. °C	70
Operating pH-range			0 - 12
Bed depth		min. mm	800
Specific pressure drop	(15 °C)	approx. kPa*h/m ²	1.0
Pressure drop		max. kPa	200
Linear velocity	operation	max. m/h	60***
Regenerant			NaOH
Counter current regeneration	level	approx. g/l	50
WS-System	concentration	approx. wt. %	2 - 4
Linear velocity	regeneration	approx. m/h	5
Co current regeneration	level	approx. g/l	100
Co current regeneration	concentration	approx. wt. %	3 - 5
Linear velocity	regeneration	approx. m/h	5
Linear velocity	rinsing	approx. m/h	5
Linear velocity	backwash (20 °C)	approx. m/h	7
Bed expansion	(20 °C, per m/h)	approx. vol. %	11
Freeboard	backwash (extern / intern)	vol. %	80 - 100
Linear velocity	rinsing	approx. m/h	5
Rinse water requirement	slow / fast	approx. BV	10

* The recommended operating conditions refer to the use of the product under normal operating conditions. It is based on tests in pilot plants and data obtained from industrial applications. However, additional data are needed to calculate the resin volumes required for ion exchange units. These data are to be found in our Technical Information Sheets.

*** 100m/h for polishing

Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Lanxess Deutschland GmbH
BU LPT
D-51369 Leverkusen

lewatit@lanxess.com

www.lewatit.com
www.lanxess.com

This document contains important information
and must be read in its entirety.